



TECHNICAL DATA

Scapa 3154

PVC Single Sided Foam Tape

DESCRIPTION

SCAPA 3154 is a primarily a foam compression sealant. The product is white. The foam is open celled and is of medium hardness foam. An acrylic pressure sensitive adhesive is coated on one side, and the product has a paper release liner on the other non-adhesive face.

Scapa 3154 will act as an air/dust seal when compressed.

APPLICATIONS

- Forms a compression air / dust seal
- For preventing electrolytic corrosion
- For cushioning
- For gap filling
- For anti slip mounting

PRODUCT BENEFITS

- Minimum 50% compression required to effect a water seal
- Service temperature: -30°C to +70°C
- Application temperature: +10°C to +40°C
- Shelf life of 1 year
- Foam exhibits rapid recovery
- Coated on one side with a high quality pressure sensitive acrylic adhesive
- Good resistance to dilute acids & alkalis
- Paper release liner on the non-adhesive face, reducing dimensional change during application
- Very good Ultra violet {UV} Light resistant
- Resistance to abrasion, corrosion and moisture
- Suitable for indoor and outdoor environments
- No known hazards associated with this product
- Pre-determined dimensional sealant reduces waste
- Clean to use, clean edge finish

ACCREDITATIONS

- Conforms to European Directive 2000/53 EC (lead, chromium VI, mercury, cadmium free)

TECHNICAL PROPERTIES

	Unit	Nominal Value	Test Method
Shore Hardness {00} Scale	"00"	25	Scapa F16
Force To Compress By 50%	Ncm ⁻²	1.7	Scapa F4
Compression Deflection After 1 Minute	Ncm ⁻²	1.1	Scapa F4
10 Minute 180° Peel Adhesion	N/25mm	5	Scapa F9
Tensile Strength	N/cm ⁻²	40	Scapa F17
Elongation At Break	%	>159	Scapa F17
Thermal Conductivity (k)	Wm ⁻¹ K ⁻¹	0.063	Lee's Disc

STANDARD PRESENTATION

- Formats : Logs, Rolls, Die Cuts, Spools
- Thickness : 3.0; 4.5; 6.0; 12.0 mm
- Core : 76 mm plastic core

RECOMMENDATIONS

Surfaces must be clean, dry, free from grease and dirt.

Recommended cleaning agent is Propan-2-ol, {IPA}. Please note manufacturer's safety instructions should be followed and customers are recommended to ensure compatibility of the solvent with their substrate.

Ideal bonding substrates are those which are: clean, dry, flat, smooth, dust free & non-porous.

Low temperatures may increase the risk of condensation, reducing the tack of the product.

Life expectancy will vary with temperature and humidity.

Product may be applied by hand direct from a roll applying even pressure.

Customers are recommended to make their own assessment of our products under their own conditions, for their own requirements.